ASTM A179 quick facts

astm-a179

Item	Engineering information
Active edition	ASTM A179 / ASTM A179 M-24
Product	Seamless cold-drawn low-carbon steel tube
Wall basis	Minimum wall thickness
OD range	3.2–76.2 mm
Main use	Heat exchangers, condensers and similar apparatus
Final heat treatment	At 650°C [1200°F] or higher after final cold draw

Project page: https://niktrd.com/astm-a179

ASTM source / basis: ASTM International — ASTM A179/A179M-24; ASTM A450/A450M-25a.