

ASTM A210 quick facts

astm-a210

Item	Engineering information
Active edition	ASTM A210 / ASTM A210M -26
Product	Seamless medium-carbon steel tube
Wall basis	Minimum wall thickness
Grades	Grade A-1 and Grade C
Common OD range	12.7–127 mm
Common wall range	0.9–12.7 mm
General requirements	ASTM A450 / ASTM A450M

ASTM source / basis: ASTM International — ASTM A210/A210M-26; ASTM A450/A450M-25a.