

Chemical composition

astm-a210

Grade	Carbon (C)	Manganese (Mn)	Phosphorus (P)	Sulfur (S)	Silicon (Si)
A-1	≤ 0.27%	≤ 0.93%	≤ 0.035%	≤ 0.035%	≥ 0.10%
C	≤ 0.35%	0.29–1.06%	≤ 0.035%	≤ 0.035%	≥ 0.10%

ASTM source / basis: ASTM International — ASTM A210/A210M-26; ASTM A450/A450M-25a.