Mechanical properties

astm-a53

Grade	Minimum tensile strength (TS)	Minimum yield strength (YS)
Grade A	330 MPa	205 MPa
Grade B	415 MPa	240 MPa

ASTM source / basis: ASTM International — ASTM A53/A53M-24.